



# Chemical resistance guide

<b>LEVEL 0</b>	<b>LEVEL 1</b>	<b>LEVEL 2</b>	<b>LEVEL 3</b>	<b>LEVEL 4</b>	<b>LEVEL 5</b>	<b>LEVEL 6</b>
< 10 min	10 > 29 min	30 > 59 min	60 > 119 min	120 > 239 min	240 > 479 min	> 480 min

## SHIELDskin XTREME™ White Nitrile 300 DI++



- Length: 305 mm/ 12.0"
- Palm thickness: 0.14 mm/ 5.5 mil
- Chemical performance: Type B / Low chemical splash protection
- Biological risk: AQL 1.5 / Level 2
- Particles level: < 850 particles/cm<sup>2</sup> > 0.5 µm / 600 particles
- Virus resistant
- Allergies: Latex-free / Accelerator-free
- Design: Ambidextrous / Powder-free
- Colour: White
- ESD - Static dissipative / Silicone-free
- Mechanical risk: N/A
- Applications: Cleanroom

64-19-7 Acetic acid 99%	<b>LEVEL 0</b> 7 min
7664-93-9 Sulphuric Acid 50%	<b>LEVEL 6</b> 480 min
75-59-2 Tetramethylammonium hydroxide 2.5%	<b>LEVEL 6</b> 480 min
108-94-1 Cyclohexanone 99%	<b>LEVEL 0</b> 6 min
67-63-0 Isopropanol 70%	<b>LEVEL 3</b> 85 min
1330-20-7 Xylene 98.5%	<b>LEVEL 0</b> 1 min
1310-73-2 Sodium Hydroxide 40%	<b>LEVEL 6</b> 480 min DR -14%

67-63-0 Isopropanol 100%	LEVEL 2 49 min
7722-84-1 Hydrogen peroxide 30%	LEVEL 6 480 min DR 19%
7664-39-3 Hydrofluoric acid 40%	LEVEL 1 11 min
7647-01-0 Hydrochloric acid 37%	LEVEL 4 129 min
50-00-0 Formaldehyde 37%	LEVEL 6 480 min DR 15%
1239-45-8 Ethidium bromide 5%	LEVEL 6 480 min
64-17-5 Ethanol 70%	LEVEL 2 35 min
64-17-5 Ethanol 99.8%	LEVEL 1 17 min
71-36-3 Butanol 100%	LEVEL 2 43 min
1336-21-6 Ammonium hydroxide 25%	LEVEL 1 29 min
79-06-1 Acrylamide 40%	LEVEL 6 480 min

DISCLAIMER: The data provided was based on gloves tested under laboratory conditions, in accordance with EN 16523-1:2015 (formerly EN 374-3:2003) and EN 374-4:2013. The information is for guidance only and may not reflect the user's application. A risk assessment should always be made by purchaser to assess the suitability of gloves for a specific application.