




# Chemical resistance guide

<b>LEVEL 0</b>	<b>LEVEL 1</b>	<b>LEVEL 2</b>	<b>LEVEL 3</b>	<b>LEVEL 4</b>	<b>LEVEL 5</b>	<b>LEVEL 6</b>
< 10 min	10 > 29 min	30 > 59 min	60 > 119 min	120 > 239 min	240 > 479 min	> 480 min

## SHIELDskin XTREME™ Sterile White Nitrile 400 DI+



- Length: 400 mm/ 15.7"
- Palm thickness: 0.15 mm/ 5.9 mil
- Chemical performance: Type B
- Biological risk: AQL 0.65 / Level 3
- Particles level: < 1,200 particles/cm<sup>2</sup> > 0.5 µm / 1,000 particles
- Sterile / Virus resistant / Chemotherapy drugs
- Allergies: Latex-free / Accelerator-free
- Design: Hand-specific / Powder-free
- Colour: White
- Silicone-free
- Mechanical risk: N/A
- Applications: Cleanroom

Mixed Solution SPOR-KLENZ Solution	<b>LEVEL 6</b> 480 min
64-19-7 Acetic acid 99%	<b>LEVEL 0</b> 6 min
7722-84-1 Hydrogen peroxide 30%	<b>LEVEL 6</b> 480 min DR -10%
Mixed Solution Perform sterile PAA ready to use	<b>LEVEL 6</b> 480 min
Mixed Solution Perform sterile concentrate PAA 3%	<b>LEVEL 6</b> 480 min
Mixed Solution Perform sterile concentrate Oxy 2%	<b>LEVEL 6</b> 480 min
7664-93-9 Sulphuric Acid 50%	<b>LEVEL 6</b> 480 min

7664-93-9 Sulphuric Acid 95%-98%	LEVEL 0 7 min
67-68-5 Dimethyl sulfoxide 99% (DMSO)	LEVEL 2 37 min
67-64-1 Acetone 99.8%	LEVEL 0 1 min
67-63-0 Isopropanol 70%	LEVEL 3 113 min
1310-73-2 Sodium Hydroxide 40%	LEVEL 6 480 min DR -70%
75-09-2 Dichloromethane 99%	LEVEL 0 0 min
67-63-0 Isopropanol 100%	LEVEL 2 43 min
7664-39-3 Hydrofluoric acid 40%	LEVEL 1 12 min
111-30-8 Glutaraldehyde 25%	LEVEL 6 480 min
50-00-0 Formaldehyde 37%	LEVEL 6 480 min DR -5%
1239-45-8 Ethidium bromide 5%	LEVEL 6 480 min
64-17-5 Ethanol 70%	LEVEL 2 46 min
64-17-5 Ethanol 99.8%	LEVEL 1 17 min
109-89-7 Diethylamine 99.5%	LEVEL 0 0 min

110-82-7 Cyclohexane	<b>LEVEL 6</b> 480 min
1336-21-6 Ammonium hydroxide 25%	<b>LEVEL 1</b> 27 min
79-06-1 Acrylamide 40%	<b>LEVEL 6</b> 480 min
75-05-8 Acetonitrile 99.9%	<b>LEVEL 0</b> 1 min

DISCLAIMER: The data provided was based on gloves tested under laboratory conditions, in accordance with EN 16523-1:2015 (formerly EN 374-3:2003) and EN 374-4:2013. The information is for guidance only and may not reflect the user's application. A risk assessment should always be made by purchaser to assess the suitability of gloves for a specific application.