




Chemical resistance guide

LEVEL 0	LEVEL 1	LEVEL 2	LEVEL 3	LEVEL 4	LEVEL 5	LEVEL 6
< 10 min	10 > 29 min	30 > 59 min	60 > 119 min	120 > 239 min	240 > 479 min	> 480 min

SHIELDskin XTREME™ White Nitrile 400 DI+



- Length: 400 mm/ 15.7"
- Palm thickness: 0.15 mm/ 5.9 mil
- Chemical performance: Type B
- Biological risk: AQL 1.5 / Level 2
- Particles level: < 1,200 particles/cm² > 0.5 µm / 1,000 particles
- Virus resistant / Chemotherapy drugs
- Allergies: Latex-free / Free of Thiazoles and Thiurams
- Design: Ambidextrous / Powder-free
- Colour: White
- ESD - Static dissipative / Silicone-free
- Mechanical risk: N/A
- Applications: Cleanroom

108-24-7 Acetic anhydride	LEVEL 0 6 min
7722-84-1 Hydrogen peroxide 30%	LEVEL 6 480 min DR 27%
1336-21-6 Ammonium hydroxide 28-30%	LEVEL 1 29 min
143-33-9 Sodium cyanide	LEVEL 6 480 min
7664-93-9 Sulphuric Acid 50%	LEVEL 6 480 min
7681-52-9 Sodium Hypochlorite 13%	LEVEL 6 480 min
1310-58-3 Potassium Hydroxide 40%	LEVEL 6 480 min

67-63-0 Isopropanol 70%	LEVEL 3 95 min
1310-73-2 Sodium Hydroxide 40%	LEVEL 6 480 min DR -12%
110-86-1 Pyridine	LEVEL 0 3 min
67-63-0 Isopropanol 100%	LEVEL 3 72 min
7664-39-3 Hydrofluoric acid 40%	LEVEL 1 15 min
7647-01-0 Hydrochloric acid 37%	LEVEL 4 157 min
50-00-0 Formaldehyde 37%	LEVEL 6 480 min DR 12%
1239-45-8 Ethidium bromide 5%	LEVEL 6 480 min
64-17-5 Ethanol 70%	LEVEL 2 52 min
64-17-5 Ethanol 99.8%	LEVEL 1 22 min
1336-21-6 Ammonium hydroxide 25%	LEVEL 2 32 min
79-06-1 Acrylamide 40%	LEVEL 6 480 min

DISCLAIMER: The data provided was based on gloves tested under laboratory conditions, in accordance with EN 16523-1:2015 (formerly EN 374-3:2003) and EN 374-4:2013. The information is for guidance only and may not reflect the user's application. A risk assessment should always be made by purchaser to assess the suitability of gloves for a specific application.