




Chemical resistance guide

| | | | | | | |
|----------------|----------------|----------------|----------------|----------------|----------------|----------------|
| LEVEL 0 | LEVEL 1 | LEVEL 2 | LEVEL 3 | LEVEL 4 | LEVEL 5 | LEVEL 6 |
| < 10 min | 10 > 29 min | 30 > 59 min | 60 > 119 min | 120 > 239 min | 240 > 479 min | > 480 min |

duoSHIELD™ PFT Nitrile 240



- Length: 240 mm/ 9.4"
- Palm thickness: 0.08 mm/ 3.1 mil
- Chemical performance: Type B
- Biological risk: AQL 0.65 / Level 3
- Particles level: N/A / N/A
- Virus resistant
- Allergies: Contains Latex protein / Free of Thiazoles and Thiurams / Powder-free
- Design: Ambidextrous / Powder-free
- Colour: Blue
- Mechanical risk: N/A
- Applications: Laboratory / General workplace / Healthcare

| | |
|--|--------------------------------------|
| 64-17-5 Ethanol 99.8% | LEVEL 1 11 min |
| 7697-37-2 Nitric acid 65% | LEVEL 0 3 min |
| 64-19-7 Acetic acid 99% | LEVEL 0 4 min |
| 7664-93-9 Sulphuric Acid 50% | LEVEL 6 480 min |
| 67-68-5 Dimethyl sulfoxide 99% (DMSO) | LEVEL 0 8 min |
| 1310-73-2 Sodium Hydroxide 40% | LEVEL 6 480 min DR -11% |
| 7722-84-1 Hydrogen peroxide 30% | LEVEL 6 480 min DR -6% |

| | |
|------------------------------------|--|
| 7647-01-0 Hydrochloric acid 37% | LEVEL 3 102 min |
| 50-00-0 Formaldehyde 37% | LEVEL 6 480 min DR -38% |
| 1239-45-8 Ethidium bromide 5% | LEVEL 6 480 min |

DISCLAIMER: The data provided was based on gloves tested under laboratory conditions, in accordance with EN 16523-1:2015 (formerly EN 374-3:2003) and EN 374-4:2013. The information is for guidance only and may not reflect the user's application. A risk assessment should always be made by purchaser to assess the suitability of gloves for a specific application.