




# Chemical resistance guide

<b>LEVEL 0</b>	<b>LEVEL 1</b>	<b>LEVEL 2</b>	<b>LEVEL 3</b>	<b>LEVEL 4</b>	<b>LEVEL 5</b>	<b>LEVEL 6</b>
< 10 min	10 > 29 min	30 > 59 min	60 > 119 min	120 > 239 min	240 > 479 min	> 480 min

## duoSHIELD™ PFT Nitrile 290



- Length: 290 mm/ 11.4"
- Palm thickness: 0.08 mm/ 3.1 mil
- Chemical performance: Type B / High chemical protection
- Biological risk: AQL 0.65 / Level 3
- Particles level: N/A / N/A
- Virus resistant / Chemotherapy drugs
- Allergies: Latex-free / Free of Thiazoles
- Design: Ambidextrous / Powder-free
- Colour: Blue
- Mechanical risk: N/A
- Applications: Laboratory / General workplace / Healthcare

7697-37-2 Nitric acid 65%	<b>LEVEL 0</b> 3 min
64-19-7 Acetic acid 99%	<b>LEVEL 0</b> 4 min
7664-93-9 Sulphuric Acid 50%	<b>LEVEL 6</b> 480 min
67-68-5 Dimethyl sulfoxide 99% (DMSO)	<b>LEVEL 0</b> 8 min
1330-20-7 Xylene 98.5%	<b>LEVEL 0</b> 0 min
1310-73-2 Sodium Hydroxide 40%	<b>LEVEL 6</b> 480 min DR -11%
7722-84-1 Hydrogen peroxide 30%	<b>LEVEL 6</b> 480 min DR -6%

7647-01-0 Hydrochloric acid 37%	<b>LEVEL 3</b> 102 min
50-00-0 Formaldehyde 37%	<b>LEVEL 6</b> 480 min DR -38%
1239-45-8 Ethidium bromide 5%	<b>LEVEL 6</b> 480 min
64-17-5 Ethanol 99.8%	<b>LEVEL 1</b> 11 min

DISCLAIMER: The data provided was based on gloves tested under laboratory conditions, in accordance with EN 16523-1:2015 (formerly EN 374-3:2003) and EN 374-4:2013. The information is for guidance only and may not reflect the user's application. A risk assessment should always be made by purchaser to assess the suitability of gloves for a specific application.