

## ORANGE BIOLOGICAL RISK

## SHIELDskin<sup>™</sup> ORANGE NITRILE™ 260











- ⇒ Powder-free ambidextrous extra length (260 mm / 10.2") non-sterile nitrile/neoprene protective gloves.
- ⇒ Personal Protective Equipment Category III (PPE Complex Design) according to Regulation (EU) 2016/425.
- ⇒ Medical Device Class 1 (MDR) according to the Regulation (EU) 2017/745.
- ⇒ Fully compliant to the latest EU PPE norms relating to protective gloves against chemicals, micro-organisms and viruses.

| DESCRIPTION |  |
|-------------|--|
| Formulation | Nitrile and neoprene synthetic rubber (acrylonitrile butadiene and polychloroprene). |
| Design      | Orange, ambidextrous, beaded cuff, textured fingertips.                              |
| Packaging   | 90 gloves per dispenser - 10 dispensers per carton.                                  |

| SIZES | 6/XS    | 7/S     | 8/M     | 9/L     | 10/XL   |
|-------|---------|---------|---------|---------|---------|
| Codes | 67 6231 | 67 6232 | 67 6233 | 67 6234 | 67 6235 |

| STANDARDS       |  |
|-----------------|--|
| CE registration | PPE Category III (Complex Design) - Regulation (EU) 2016/425.<br>Notified Body No 0598: SGS Fimko Oy, Helsinki - FINLAND.<br>MDR Class 1 - Regulation (EU) 2017/745. |
| EU PPE norms    | ISO 21420:2020, EN 421:2010, ISO 374-1:2016+A1:2018, ISO 374-2:2019, ISO 374-4:2019, ISO 374-5:2016, EN 16523-1:2015+A1:2018 and ISO 16604:2004 Procedure B.         |
| EU MDR norms    | EN 455-1:2020, EN 455-2:2015, EN 455-3:2015 and EN 455-4:2009.   |
| USA standards   | ASTM D3767-03 (2020), ASTM D573-04 (2019), ASTM D412-16, ASTM D6978-05 (2019).   |
| Other standards | EN1149-1/2/3 & 5, ISO 21171:2006, ISO 10993-10:2010.   |

| QUALITY           |   |
|-------------------|---|
| Quality assurance | Production management in accordance with ISO 9001:2015 and ISO 13485:2016. Environmental management systems in accordance with ISO 14001:2015.  |
| Technology        | twinSHIELD™ double-walled protection to offer a stronger glove and to reduce risk of pinholes.  Two colours: orange to make it easier to select according to the risk, combined with a soft and comfortable white interior. |

| DOCUMENTATION             |  |                 |
|---------------------------|--|-----------------|
| Declaration of conformity | These documents can be freely downloaded from the product page on our website: www.shieldscientific.com. | 回数数2回<br>图28/32 |
| EU type examination       | For easy access, scan the QR code.   | No.             |
| User's instructions       |  |                 |

## PHYSICAL PROPERTIES



0.14<sub>mm</sub>
5.5<sub>mil</sub>

10.2<sub>in.</sub>

AQL 0.25

| NOI           | MINAL THICKNESS | mm <sup>1</sup> | mil | Norm                 |
|---------------|-----------------|-----------------|-----|----------------------|
| $\Rightarrow$ | Finger          | 0.17            | 6.7 |                      |
| $\Rightarrow$ | Palm            | 0.14            | 5.5 | ASTM D3767-03 (2020) |
| $\Rightarrow$ | Cuff            | 0.10            | 3.9 |                      |

<sup>&</sup>lt;sup>1</sup> Thickness (+/- 0.03 mm)

| LENGTH                                   | Minimum          | Typical        | Norm           |
|--|------------------|----------------|----------------|
| ⇒ From middle finger tip to edge of cuff | ≥ 260 mm / 10.2" | 265 mm / 10.4" | ISO 21420:2020 |

|               | RENGTH<br>DPERTIES | Force<br>at break<br>(spec.) | Ultimate elongation (spec.) | Force at<br>break<br>(typical) | Norm                                  |
|---------------|--------------------|------------------------------|-----------------------------|--------------------------------|---------------------------------------|
| $\Rightarrow$ | Before aging       | ≥ 6.0N 14 MPa                | ≥ 500%                      | 10.0N                          | EN 455-2:2015                         |
| $\Rightarrow$ | After aging        | ≥ 6.0N 14 MPa                | ≥ 400%                      | 8.0N                           | ASTM D573-04 (2019)<br>& ASTM D412-16 |

| FREEDOM FROM HOLES               | Performance                   | Norm                            |
|----------------------------------|-------------------------------|---------------------------------|
| ⇒ Acceptable Quality Level (AQL) | < 0.25 <sup>2</sup> - Level 3 | ISO 374-2:2019<br>EN 455-1:2020 |

<sup>&</sup>lt;sup>2</sup> AQL as defined per ISO 2859-1:1999 for sampling by attributes.

## PROTECTION PROPERTIES

| RISKS           | Description  | Norm  |
|-----------------|--|---|
| Micro-organisms | 1000 ml water test. Performance level 3, AQL < 0.25 (inspection level G1).   | ISO 374-2:2019  |
| Viruses         | Viral penetration test using Phi-X174 bacteriophage according to ISO 16604:2004 Procedure B.   | ISO 374-5:2016  |
| Chemicals       | Performance: Type B (JKPT). Permeation: Extensively tested. Online chemical resistance guide on www.shieldscientific.com. Degradation: Tested for determination of resistance to degradation by chemicals. | ISO 374-1:2016+A1:2018<br>EN 16523-1:2015+A1:2018<br>ISO 374-4:2019 |
| Radioactivity   | Protection from radioactive contamination.   | EN 421:2010   |
| Cytotoxic       | Tested for permeation to potentially hazardous cancer chemotherapy drugs under conditions of continuous contact.   | ASTM D6978-05 (2019)  |
| ESD             | Tested for electrostatic properties.   | EN 1149-1/2/3 & 5   |

| ALLERGIES          |   |
|--------------------|---|
| Bio-compatibility  | Demonstrated by skin irritation and sensitization tests in accordance with ISO 10993-10:2010.   |
| Accelerators       | Accelerator-free to minimize the risk of allergic contact dermatitis (also known as Type IV, delayed hypersensitivity or chemical allergy).                                     |
| Chemical allergens | Non-detectable levels using aqueous solution extraction (Phosphate buffered solution) and High Performance Liquid Chromatography (HPLC) assay method for quantitative analysis. |
| Residual powder    | Powder-free to minimize the potential consequences of powder-borne dermatitis. Residual powder content is 1.0 mg/glove (typical) with a limit of 2.0 mg/glove (ISO 21171:2006). |
| Latex protein      | Latex-free.   |
|                    |   |

