

## CHEMICAL RESISTANCE DATA



# SHIELDskin XTREME™

## SHIELDskin Xtreme Bright Latex 300 DI+



- Cleanroom glove - PPE Complex Design (Category III)
- 100% Natural Latex glove - Powder Free
- Ambidextrous - Fully Textured
- AQL 1.5 (EN374-2:2003 Level 2)
- Length 300 mm
- Reduced allergy risks (Type I and Type IV)
- Virus and Microorganism resistant (ASTM F1671-97b and EN374-2:2003)
- Typical particle levels: less than 950 per cm<sup>2</sup> more or equal 0,5µm

1239-45-8	Ethidium bromide 5%	Breakthrough time : 480 minutes	Class 6
1310-73-2	Sodium Hydroxide, 40%	Breakthrough time : 480 minutes	Class 6
7664-93-9	Sulphuric acid, 50%	Breakthrough time : 480 minutes	Class 6
79-06-1	Acrylamide 40%	Breakthrough time : 480 minutes	Class 6
67-68-5	Dimethyl Sulfoxide 99% (DMSO)	Breakthrough time : 93 minutes	Class 3
7647-01-0	Hydrochloric Acid, 37%	Breakthrough time : 44 minutes	Class 2
7722-84-1	Hydrogen Peroxide, 30%	Breakthrough time : 43 minutes	Class 2
7697-37-2	Nitric Acid, 50%	Breakthrough time : 27 minutes	Class 1
7664-39-3	Hydrofluoric Acid, 48%	Breakthrough time : 26 minutes	Class 1
67-63-0	Isopropanol 70%	Breakthrough time : 11 minutes	Class 1
1336-21-6	Ammonium Hydroxide, 25%	Breakthrough time : 9 minutes	Class 0
67-63-0	Isopropanol 100%	Breakthrough time : 7 minutes	Class 0
64-17-5	Ethanol, 70%	Breakthrough time : 5 minutes	Class 0
64-17-5	Ethanol 100%	Breakthrough time : 4 minutes	Class 0
67-64-1	Acetone 100%	Breakthrough time : 1 minutes	Class 0
1330-20-7	Xylene 98,5%	Breakthrough time : 0 minutes	Class 0
67-56-1	Methanol 99,9%	Breakthrough time : 0 minutes	Class 0