

CHEMICAL RESISTANCE DATA



ecoSHIELD™

ecoSHIELD ECO LATEX PF 250



- PPE glove - Complex Design (Category III)
- 100% Natural Latex glove - Powder Free
- Unique Latex formulation
- Ambidextrous -Textured finger tips
- AQL 0,65 (EN374-2:2003 Level 3)
- Length 250 mm / Thickness 0,15 mm (Fingertip) (EN420:2003)
- Reduced allergy risks (Type I & Type IV)
- Virus and Microorganisms resistant glove (ASTM F1671-97b and EN374-2:2003)

1239-45-8	Ethidium bromide 5%	Breakthrough time : 480 minutes	Class 6
1310-73-2	Sodium Hydroxide, 50%	Breakthrough time : 480 minutes	Class 6
7664-93-9	Sulphuric acid, 50%	Breakthrough time : 480 minutes	Class 6
79-06-1	Acrylamide 40%	Breakthrough time : 480 minutes	Class 6
67-68-5	Dimethyl Sulfoxide 99% (DMSO)	Breakthrough time : 151 minutes	Class 4
7647-01-0	Hydrochloric Acid, 37%	Breakthrough time : 57 minutes	Class 2
7664-93-9	Sulphuric acid, 95-98%	Breakthrough time : 18 minutes	Class 1
67-63-0	Isopropanol 70%	Breakthrough time : 12 minutes	Class 1
1336-21-6	Ammonium Hydroxide, 25%	Breakthrough time : 7 minutes	Class 0
67-63-0	Isopropanol 100%	Breakthrough time : 7 minutes	Class 0
64-17-5	Ethanol 100%	Breakthrough time : 3 minutes	Class 0
64-19-7	Acetic Acid 100%	Breakthrough time : 3 minutes	Class 0
75-05-8	Acetonitrile 99,9%	Breakthrough time : 2 minutes	Class 0
107-13-1	Acrylonitrile 99%	Breakthrough time : 1 minutes	Class 0
1330-20-7	Xylene 98,5%	Breakthrough time : 1 minutes	Class 0
67-64-1	Acetone 100%	Breakthrough time : 1 minutes	Class 0
67-56-1	Methanol 99,9%	Breakthrough time : 0 minutes	Class 0
75-09-2	Dichloromethane 99%	Breakthrough time : 0 minutes	Class 0
80-62-6	Methyl Methacrylate 99%	Breakthrough time : 0 minutes	Class 0