

## Data sheet

Article: Glass inserts  
Code no.: 924 05 96

---

### Material:

Soda-lime glass

### Chemical properties:

- Hydrolytic resistance at 98°C: Class 3 acc. ISO 719
- Hydrolytic resistance at 121°C: Class 3 acc. ISO 720
- Acid resistance: Class 1 acc. ISO 1776
- Alkali resistance: Class 2 acc. ISO 695

### Physical properties:

- Transformation temperature: 525°C
- Permissible operation temperature: max. 350°C
- Density: 2,50 g/cm<sup>3</sup>
- Linear expansion coefficient: 9,1 x 10<sup>-6</sup> K<sup>-1</sup>

**Length:** approx. 42 mm

**Outer diameter:** approx.. 7,8 mm

**Wall thickness:** approx. 0,65 mm

Hirschmann Laborgeräte  
GmbH & Co.KG



.....  
Roland Benz  
Quality Manager

Eberstadt, 04.04.2017