

Certificate of Conformity



Article no.	Retrace Code/Batch/Lot no.	Date of Manufacture
218010802	10173203	2024-09-23

Article description

DURAN® Laboratory bottle, clear, graduated, GL 25, without cap and without pouring ring, 10 ml

DURAN® Product Certificate

The articles listed under "article number" are hereby confirmed to have been produced using a quality system conforming to ISO 9001 and comply with the DWK Life Sciences quality standards. The specified glass products are manufactured from DURAN® glass.

DURAN® glass is classified as a Borosilicate 3.3 glass as defined by ISO 3585:1998.

Prior to delivery, all production batches are subjected to statistical quality inspections corresponding to the standard DIN ISO 2859 -1. We herewith confirm that this lot passed the statistical quality inspection according to ISO 2859-1.

DURAN® – Glass type 1 Composition

SiO ₂	B ₂ O ₃	Na ₂ O/K ₂ O	Al ₂ O ₃
81 %	13 %	4 %	2 %

DURAN® - Chemical and physical properties

Coefficient of expansion	Acid resistance	Acid resistance	Hydrolytic resistance	Alkalis resistance
$3.3 \times 10^{-6} \text{ K}^{-1}$	Class S 1 (DIN 12116)	$\leq 100 \mu\text{g Na}_2\text{O per dm}^2$ (ISO 1776)	Class HGB 1 (ISO 719) / Class HGA 1 (ISO 720)	Class A 2 (ISO 695)

Certificate of Conformity



Article no.	Retrace Code/Batch/Lot no.	Date of Manufacture
218010802	10173203	2024-09-23

Directive Conformity

Due to its high hydrolytic resistance, DURAN® is a neutral glass respectively glass type I and consequently fulfills the requirements of the following pharmacopoeias:

- USP <660> Containers - Glass
- EP (3.2.1) Glass containers for pharmaceutical use

The arsenic content in DURAN® Glass is less than 0.1 ppm acc. to EP (3.2.1) and 0.1 µg per g acc. USP <660> / Arsenic <211>.

DURAN® is compliant with JP <7.01> Test for Glass Containers for Injections (Soluble Alkali).

DURAN® is certified for food applications.

All confirmations and information in this certificate apply solely to goods originating from DURAN®. For further processed products these details are not binding.

Statement on BSE/TSE for products manufactured from DURAN® glass:

We hereby confirm that DURAN® glass consists of raw material without any biological origin or genetically modified organism (GMO). No materials of animal origin are used or added during the manufacturing process.

The manufacturing of DURAN® glass involves minimum melting temperatures of 1500 °C for several hours, where all the raw materials are melted together. After forming, the glass products are tempered in an oven at more than 400 °C before being slowly cooled. Due to the high temperatures, we can act on the assumption that any and all biological substances are destroyed during production.

Therefore, DURAN® glass can be considered as free of Bovine Spongiform Encephalopathy (BSE) and Transmissible Spongiform Encephalopathy (TSE).

Please note that analysis of the raw materials and/or finished goods for presence of the above mentioned substances is not performed on a routine basis.

Certified by: 
Mariska Jefferson
Quality Manager

Download date: 2025-01-21