Certificate of Analysis

CORNING® COLLAGEN I High Concentration (HC), RAT TAIL

Collagen I is found in most tissues and organs, but is most plentiful in dermis, tendon and bones. Type I molecule is a heterotrimer [alpha $_1$ (I) $_2$ alpha $_2$ (I)] of 300 nm length being composed of two alpha $_1$ (I) chains and one alpha $_2$ (I) chain. Collagen binding integrin receptors are alpha $_1$ Beta $_1$, alpha $_2$ Beta $_1$, and alpha $_3$ Beta $_1$. When used as a gel, collagen facilitates successful adaptation *in vitro* culture and enhances expression of cell-specific morphology and function. The Collagen HC is used in applications where a sturdy gel provides maximal support to maintain the three dimensional structure. $^{3-5}$

CATALOG NUMBER:	354249	LOT NUMBER:				
SOURCE:	Rat tail tendon					
QUANTITY:	100 milligrams protein (measured by Pyrochemiluminescence)					
CONCENTRATION:	mg/mL					
FORMULATION:	0.02 N Acetic Acid					
USE:	reverse for gelling procedures. Use	sed as a three dimensional gel. Please see these as guidelines only - we recommend etermine the optimal conditions for their				
QUALITY CONTROL:	≥ 90 % by SDS PAGE.					
	This product has been tested for its ability to promote the attachment and spreading of HT-1080 Human Fibrosarcoma cells.					
	Corning Collagen I HC, rat tail, is a membrane-filtered (0.2 micron) preparation. Tested and found negative for the presence of bacteria, fungi and mycoplasma.					
STORAGE:	Stable when stored at 2-8°C. DO NOT FREEZE .					
·	On release this product has been successfully gelled over a wide range of dilutions and will form a gel up to a concentration of 0.3 mg/mL. Further dilution may decrease the rigidity of the gel as will the time from manufacture.					
EXPIRATION DATE:						
REFERENCES:	E.D. Hay) pp 5-37, Plenum P	E., J. <i>Cell Biol.,</i> 120 :537 (1993). 6 :7300 (1999). , 14 :1299 (1999).				

Suggested Coating Procedures

Gelling Procedure- Corning Collagen I HC, rat tail, will gel when its pH is brought to alkalinity using the procedure below. Please use this as a guideline for determining the optimum concentration for your application.

1) Prepare ammonia vapor chamber by taping a sterile 2 inch gauze sponge to the inside lid of a 150 mm petri dish. Saturate the gauze with ammonium hydroxide. Place lid on 150 mm dish and set aside.

Discovery Labware, Inc., Two Oak Park, Bedford, MA 01730, Tel: 1.978.442.2200 (U.S.) CLSTechServ@Corning.com www.corning.com/lifesciences

CORNING

- 2) Place an even coating of Corning[®] Collagen I HC, rat tail, on surface to be coated. Thickness may be varied as desired. 50-100 μl of Corning Collagen I HC, rat tail, is sufficient to coat a 22 mm coverslip. For dishes of 100 mm diameter, add approximately 6.0 mL per dish; for 60 mm dishes add approximately 2.3 mL and for 35 mm dishes add approximately 1.0 mL.
- Transfer coated coverslips or dishes with lids off to ammonia vapor chamber and expose for three minutes.
- 4) Soak coated coverslip or dishes in sterile dH₂O for 30 minutes (5 mL for 35 mm dishes, 10 mL for 60 mm dishes, etc.). Aspirate and replace with 0.5-1.0 mL of sterile dH₂O and let sit overnight lidded in a laminar flow hood.
- 5) Aspirate the dH₂O and replace with serum supplemented balanced salt solution and store at 2-8°C.

Alternate Gelation Procedure for Corning Collagen I HC, Rat tail

- 1.0 Place on ice the following:
 - 1.1 Corning Collagen I HC, rat tail
 - 1.2 Sterile 10X phosphate buffered saline (10X PBS)
 - 1.3 Sterile dH₂O
 - 1.4 Sterile 1 N NaOH
- 2.0 Determine the final volume of Corning Collagen I HC, rat tail, solution to be used and the desired final collagen concentration.
- 3.0 Place on ice a sterile tube of sufficient capacity to contain the final volume of Corning Collagen I HC, rat tail.
- 4.0 Perform the following steps using aseptic technique in a Class 100 Hood.
 - 4.1 Add to the tube the following volume of 10X PBS:

Final Volume		
	= mL 10	OX PBS
10		

4.2 Calculate the volume of Corning Collagen I HC, rat tail, to be used (do not add to the tube until step 4.6):

Final volume x Final collagen concentration in mg/mL = volume collagen to be added Concentration in bottle (see lot specific spec. sheet)

4.3 Add to the 10X PBS the following volume of sterile ice cold 1 N NaOH:

(volume collagen to be added) x 0.023 mL = volume 1 N NaOH

4.4 Add to the 10X PBS/1 N NaOH the following volume of sterile ice-cold dH₂O:

(Final volume) - (Volume collagen) - (Volume 10X PBS) - (Volume 1 N NaOH) = Volume dH_2O to add

Discovery Labware, Inc., Two Oak Park, Bedford, MA 01730, Tel: 1.978.442.2200 (U.S.) CLSTechServ@Corning.com www.corning.com/lifesciences

CORNING

- 4.5 Mix the contents of tube and hold in ice.
- 4.6 Add the calculated volume of Corning[®] Collagen I HC, rat tail, and mix. Leave on ice until ready for use.
- 5.0 The Corning Collagen I HC, rat tail, solution can be used immediately or held on ice for 2-3 hours.
- 6.0 When ready to use, aseptically deliver the solution into the cell culture device and allow to gel at 37°C for 30 minutes.

NOTE: For more details on Corning Collagen products and technical resources please visit support page at www.corning.com/lifesciences

Quality Assurance			Date	

Discovery Labware, Inc., Two Oak Park, Bedford, MA 01730, Tel: 1.978.442.2200 (U.S.) CLSTechServ@Corning.com www.corning.com/lifesciences

