

# TECHNICAL DATA SHEET ITEM 916

Mod. AQ 001 Rev. 0 del 25/09/2003

## **TECHNICAL SPECIFICATIONS**

Trade name	Screw cap containers
Use	Ideal for storing mercury etc.
Material	Hight Density Polyethylene (HDPE)
Other features	Leakproof Sturdy, heavy walled with excellent chemical reistance

#### **DIMENSIONAL SPECIFICATIONS**

Capacity	ml 180
External, diameter	mm 54,5
Internal, diameter	mm. 50
Height	mm. 109,6
Wall thickness	mm. 2,2
Weight	61 g.



## **GENERAL FEATURES**

CE Mark	No	
Foodstuff suitablity	Yes	

## **STERILIZATION**

Autoclavability +121°C	No
Gas (Ethylene Oxide)	Yes
Dry Heat (+160°C)	No
Chemical (Formalin)	Yes
Irradiation	Yes
Microwave	Yes

## **CLEANING OPERATIONS**

Slight contamination	Wash with neutral detergent (pH 7)
Consistent contamination	Wash with alkalin detergent (pH up to 12)

# **Quality Assurance** Massimiliano Capitanio

**Technical Direction** 

Guido Borona



# TECHNICAL DATA SHEET ITEM 916

Mod. AQ 001 Rev. 0 del 25/09/2003

#### **CHEMICAL RESISTANCES**

Categories of substances	Reference	Concen. %	T. 20° C	T. 40° C	T. 60° C
Inorganic acid	Sulphuric acid	98	В	В	В
Organic acid	Benzoic acid	100	Α	Α	Α
Alcohol	Ethanol	100	A	Α	Α
Aldehydes	Acetaldehyde	100	Α	В	В
Inorganic alkali	Sodium hydroxide	50	Α	Α	Α
Organic alkali	Aniline	100	А	В	С
Ketone	Acetone	100			
Esther	Ethyl acetate	100	В	В	В
Hydrocarbons, halogenated	Dichloroethylene	100	В	С	
Hydrocarbons, aromatic	Benzene	100	В	В	В
Hydrocarbons, linear	Hexane	100	В	В	С
Supersolvent	Tetrahydrofuran	100	В	В	В

Legenda (not applicable if neglected):

- A: fair resistence; exposure (30 days) to the chemical does not cause any damage.
- B: sufficient resistence; exposure causes damage of poor importance, which sometimes is only temporary.
- C: poor resistence; exposure to chemical is not allowed, or causes immediate permanent damages.

Results of testing with reference materials are to be considered as indication: in case of specific use it is recommended to carry out preliminary testing.

Information about resistance of plastic materials to temperatures, steriization and washing treatments are based on bulletins issued by the Producers of raw materials , on literature data and on the experience gained in using the products

#### **PACKAGING**

Bag	Pcs 10

**Quality Assurance** Massimiliano Capitanio Technical Direction
Guido Borona

