

TECHNICAL DATA SHEET ARTICLE 500

Mod. AQ 001 Rev. 0 del 25/09/2003

TECHNICAL CHARACTERISTICS

Trade name	Forceps
Use	Self – sprung forceps with rounded ends
Material	РОМ
Other features	Autoclavable

DIMENSIONAL CHARACTERISTICS

Lengh mm	118
Colour	Yellow



GENERAL CHARACTERISTICS

CE mark	No
Foodstuff suitability	Yes

STERILIZATION

Autoclavability atT +121°C	Yes
Gas (Ethylene Oxide)	Yes
Dry at 160°C	Yes
Chemical (Formalin)	Yes
Radiations	No
Microwave	No



TECHNICAL DATA SHEET ARTICLE 500

Mod. AQ 001 Rev. 0 del 25/09/2003

CHEMICAL RESISTANCES

Categories of substances	Reference	Concentration %	T. 20° C	T. 40° C	T. 60° C
Inorganic Acid	Sulphuric acid	98	C		-
Organic Acid	Benzoic acid	100	В	В	С
Alcohol	Ethanol	100	Α	В	В
Aldehydes	Acetaldeyde	100	Α	Α	Α
Inorganic alkali	Isodium hydroxide	50	O	-	
Organic alkali	Aniline	100	Α	В	С
Ketone	Acetone	100	i	-	-
Esther	Ethyl acetate	100	В	С	=
Hydrocarbons, halogenated	Dichloroethylene	100	C		
Hydrocarbons, aromatic	Benzene	100	А	В	С
Hydrocarbons, linear	, linear Hexane		Α	Α	Α
Supersolvent	Tetrahydrofuran	100	Α	В	В

Legenda (not applicable if neglected):

- A: fair resistence; exposure (30 days) to the chemical does not cause any damage.
- B: sufficient resistence; exposure causes damage of poor importance, which sometimes is only temporary.
- C: poor resistence; exposure to chemical is not allowed, or causes immediate permanent damages.

Results of testing with reference materials are to be considered as indication: in case of specific use it is recommended to carry out preliminary testing.

Information about resistance of plastic materials to temperatures, steriization and washing treatments are based on bulletins issued by the Producers of raw materials , on literature data and on the experience gained in using the products

PACKAGING

I Dave	F
Box	15 pcs
I DOX	1 0 poo

Quality Assurance Massimiliano Capitanio

