

TECHNICAL SPECIFICATIONS

| | |
|------------|------------------|
| Trade name | Industrial scoop |
| Use | General use |
| Material | Polypropylene PP |

DIMENSIONAL SPECIFICATIONS

| | |
|------------|---------------------|
| Capacity | ml. 50 |
| Dimensions | mm. 55,4 x 163 x 26 |



GENERAL FEATURES

| | |
|-----------------------|-----|
| CE mark | No |
| Food contact suitable | Yes |

STERILIZATION

| | |
|-------------------------|-----|
| Autoclavability + 121°C | Yes |
| Gas (Ethylene Oxide) | Yes |
| Dry Heat (+160°C) | No |
| Chemical (Formalin) | Yes |
| Irradiation | Yes |
| Microwave | Yes |

CLEANING OPERATIONS

| | |
|--------------------------|--|
| Slight contamination | Wash with neutral detergent (pH 7) |
| Consistent contamination | Wash with alkaline detergent (pH up to 12) |

Quality Assurance

Massimiliano Capitanio

Technical Direction

Guido Borona

CHEMICAL RESISTANCE

| Categories of substances | Reference | Concen. % | T. 20° | T. 40° | T.° 60 |
|---------------------------|------------------|-----------|--------|--------|--------|
| Inorganic acid | Sulphuric acid | 98 | B | C | - |
| Organic acid | Benzoic acid | 100 | A | B | B |
| Alcohol | Ethanol | 100 | A | A | A |
| Aldehydes | Acetaldehyde | 100 | B | C | - |
| Inorganic alkali | Sodium hydroxide | 50 | A | A | A |
| Organic alkali | Aniline | 100 | A | B | C |
| Ketone | Acetone | 100 | - | - | - |
| Esther | Ethyl acetate | 100 | B | B | C |
| Hydrocarbons, halogenated | Dichloroethylene | 100 | C | - | - |
| Hydrocarbons, aromatic | Benzene | 100 | B | C | - |
| Hydrocarbons, linear | Hexane | 100 | B | B | C |
| Supersolvent | Tetrahydrofuran | 100 | B | B | C |

Legenda (not applicable if neglected):

- **A: fair resistance;** exposure (30 days) to the chemical does not cause any damage.
- **B: sufficient resistance;** exposure causes damage of poor importance, which sometimes is only temporary.
- **C: poor resistance;** exposure to chemical is not allowed, or causes immediate permanent damage.

Results of testing with reference materials are to be considered as indication: in case of specific use it is recommended to carry out preliminary testing..

PACKAGING

| | |
|-----|--------|
| Box | Pcs 12 |
|-----|--------|

Quality Assurance

Massimiliano Capitanio

Technical Direction

Guido Borona

DOMINIQUE DUTSHER SAS