

<b>Kartell SpA</b> DIVISIONE LABWARE	<b>TECHNICAL DATA SHEET</b> <b>ITEM 920</b>	Mod. AQ 001 Rev. 0 del 25/09/2003
---	--	--------------------------------------

### TECHNICAL SPECIFICATIONS

<b>Trade name</b>	Dust cover for item code 921
<b>Use</b>	Protects the place slide storage from dust and external contamination
<b>Raw material</b>	PS
<b>Other characteristics</b>	Transparent lid

### DIMENSIONAL SPECIFICATIONS

<b>Length</b>	mm. 345,00
<b>Width</b>	mm. 35,00
<b>Height</b>	mm. 40,00
<b>General dimensional tolerance</b>	mm. +/- 0,50



### GENERAL FEATURES

<b>CE mark</b>	No
<b>Food contact</b>	n.a.

### STERILIZATION PS

<b>Autoclavability at +121°C</b>	No
<b>Gas (Ethylene Oxide)</b>	Yes
<b>Dry at 160°C</b>	No
<b>Chemical (Formalin)</b>	Yes
<b>Radiations</b>	Yes
<b>Microwave</b>	No

### Assicurazione Qualità

Massimiliano Capitanio

<b>Kartell SpA</b> DIVISIONE LABWARE	<b>TECHNICAL DATA SHEET</b> <b>ITEM 920</b>	Mod. AQ 001 Rev. 0 del 25/09/2003
---	--	--------------------------------------

### CLEANING OPERATIONS

Slight contamination	Wash with neutral detergent (pH 7)
Consistent contamination	Wash with alkaline detergent (pH up to 12)

### CHEMICAL RESISTANCES

Categories of substances	Reference	Concen. %	T. 20°	T. 40°	T. ° 60
Inorganic acid	Sulphuric acid	98	C	-	-
Organic acid	Benzoic acid	100	B	B	B
Alcohol	Ethanol	100	B	C	-
Aldehydes	Acetaldehyde	100	C	-	-
Inorganic alkali	Sodium hydroxide	50	A	A	A
Organic alkali	Aniline	100	C	-	-
Ketone	Acetone	100	-	-	-
Esther	Ethyl acetate	100	C	-	-
Hydrocarbons, halogenated	Dichloroethylene	100	C	-	-
Hydrocarbons, aromatic	Benzene	100	C	-	-
Hydrocarbons, linear	Hexane	100	C	-	-
Supersolvent	Tetrahydrofuran	100	C	-	-

**Legenda** (not applicable if neglected):

- **A: fair resistance;** exposure (30 days) to the chemical does not cause any damage.
- **B: sufficient resistance;** exposure causes damage of poor importance, which sometimes is only temporary.
- **C: poor resistance;** exposure to chemical is not allowed, or causes immediate permanent damage.

**Results of testing with reference materials are to be considered as indication: in case of specific use it is recommended to carry out preliminary testing.**

### PACKAGING

Bag	Pcs. 2
Case	Pcs. 90

**Assicurazione Qualità**

Massimiliano Capitanio