

### TECHNICAL FEATURE

<b>Trade name</b>	Overturnable septa
<b>Use</b>	Pierceable stoppers to withdraw solutions and suspensions from closed containers using syringes. Suitable for use in food and beverage industry
<b>Material</b>	Sylicon

### DIMENSIONAL FEATURES

<b>Height of overturnable section</b>	20 mm
<b>Height of lower section</b>	10 mm
<b>Lower diameter</b>	13 mm
<b>N/S</b>	-



### GENERAL FEATURES

<b>CE Mark</b>	No
<b>Foodstuff suitability</b>	Yes

### STERILIZATION

<b>Autoclavability + 121°C</b>	Yes
<b>Gas (Ethylene Oxide)</b>	Yes
<b>Dry Heat (+160°C)</b>	Yes
<b>Chemical (Formalin)</b>	Yes
<b>Irradiation</b>	No
<b>Microwave</b>	Yes

**Quality Manager**  
Massimiliano Capitanio

**CLEANING OPERATIONS**

<b>Slight contamination</b>	Wash with chemically neutral detergent (pH7)
<b>Heavy contamination</b>	Wash with alkaline cleaning agents (pH up to 12)

**CHEMICAL RESISTANCE**

Categories of substances	Reference	Concen. %	T. 20°	T. 40°	T.° 60
<b>Inorganic acid</b>	Sulphuric acid	98	C	-	-
<b>Organic acid</b>	Benzoic acid	100	B	B	C
<b>Alcohol</b>	Ethanol	100	B	B	C
<b>Aldehydes</b>	Acetaldehyde	100	C	-	-
<b>Inorganic alkali</b>	Sodium hydroxide	50	A	B	C
<b>Organic alkali</b>	Aniline	100	C	-	-
<b>Ketone</b>	Acetone	100	C	-	-
<b>Esther</b>	Ethyl acetate	100	C	-	-
<b>Hydrocarbons, halogenated</b>	Dichloroethylene	100	C	-	-
<b>Hydrocarbons, aromatic</b>	Benzene	100	C	-	-
<b>Hydrocarbons, linear</b>	Hexane	100	C	-	-
<b>Supersolvent</b>	Tetrahydrofuran	100	C	-	-

**Legenda** (not applicable if neglected):

- **A: fair resistance;** exposure (30 days) to the chemical does not cause any damage.
- **B: sufficient resistance;** exposure causes damage of poor importance, which sometimes is only temporary.
- **C: poor resistance;** exposure to chemical is not allowed, or causes immediate permanent damage.

Results of testing with reference materials are to be considered as indication: in case of specific use it is recommended to carry out preliminary testing.

Information about resistance of plastic materials to temperatures, steriization and washing treatments are based on bulletins issued by the Producers of raw materials , on literature data and on the experience gained in using the products.

**PACKAGING**

<b>Box</b>	30 pcs
------------	--------

**Quality Manager**  
Massimiliano Capitanio

**DOMINIQUE DUTSHER SAS**