

TECHNICAL DATA SHEET ITEM 2489

Mod. AQ 001 Rev. 0 del 25/09/2003

TECHNICAL SPECIFICATIONS

| Trade name | Volumetric Flasks with cap |
|------------|---|
| Use | No meniscus; calibrated gravimetrically; autoclavable |
| Material | PMP (TPX®) |
| Others | Conforms to NS/DIN 19/26 |

DIMENSIONAL SPECIFICATIONS

| Height | mm. 325,00 |
|-------------------------------|--------------|
| External base, diameter | mm. 120,00 |
| General dimensional tolerance | mm. +/- 0,10 |
| Capacity | ml. 1000 |



GENERAL FEATURES

| CE mark | No |
|-----------------------|-----|
| Food contact suitable | Yes |

STERILIZATION

| Autoclavability at +121°C | Yes |
|---------------------------|-----|
| Gas (Ethylene Oxide) | Yes |
| Dry at 160°C | No |
| Chemical (Formalin) | Yes |
| Radiations | No |
| Microwave | Yes |

CLEANING OPERATIONS

| Slight contamination | Wash with neutral detergent (pH 7) | | |
|--------------------------|--|--|--|
| Consistent contamination | Wash with alkaline detergent (pH up to 12) | | |

Quality Assurance

Massimiliano Capitanio



TECHNICAL DATA SHEET ITEM 2489

Mod. AQ 001 Rev. 0 del 25/09/2003

CHEMICAL RESISTANCE

| Categories of substances | Reference | Concen. % | T. 20° | T. 40° | T.° 60 |
|--------------------------|-------------------|-----------|--------|--------|--------|
| Inorganic acid | Sulphuric acid | 98 | В | В | В |
| Organic acid | Benzoic acid | 100 | A | В | В |
| Alcohol | Ethanol | 100 | Α | В | В |
| Aldehydes | Acetaldehyde | 100 | В | C | - |
| Inorganic alkali | Sodium hydroxide | 50 | Α | Α | Α |
| Organic alkali | Aniline | 100 | В | В | С |
| Ketone | Acetone | 100 | В | С | |
| Esther | Ethyl acetate | 100 | Α | Α | Α |
| Hydrocarbons, | Dichloroethylene | 100 | | _ | _ |
| halogenated | Dictriordentylene | 100 | C | _ | |
| Hydrocarbons, aromatic | Benzene | 100 | В | С | - |
| Hydrocarbons, linear | Hexane | 100 | В | С | - |
| Supersolvent | Tetrahydrofuran | 100 | В | В | O |

Legenda (not applicable if neglected):

- A: fair resistence; exposure (30 days) to the chemical does not cause any damage.
- **B: sufficient resistence**; exposure causes damage of poor importance, which sometimes is only temporary.
- **C: poor resistence;** exposure to chemical is not allowed, or causes immediate permanent damage.

Results of testing with reference materials are to be considered as indication: in case of specific use it is recommended to carry out preliminary testing.

PACKAGING

| Bag | Pcs. 5 |
|-----|---------|
| Вох | Pcs. 60 |

Quality Assurance

Massimiliano Capitanio

