



Whatman™ Grade QM-H Quartz Filter

Data for Grade QM-H Quartz Filter paper*

Grade	QM-H
Weight	85 g/m ²
Thickness	0.43 mm
Density	200 kg/m ³
Dry tensile strength MD/CD	200/100 N/m
Pressure drop (5.3 cm/s)	450 Pa
Penetration (0.3 µm, at 15 cm/s)	< 0.002%

Typical trace elements, levels (ppm)	Al	As	Cd	Co	Cr	Cu	Fe	Hg	Mg
	50	< 0.75	1.5	1.0	5.0	1.25	30	< 0.05	25
	Mn	Na	Ni	Pb	Sb	Sn	Ti	V	Zn
	1.25	40	2.0	0.75	1.25	0.5	2.5	0.5	5.0

* Data represent typical average values.

www.gelifesciences.com

GE, GE Monogram, and Whatman are trademarks of General Electric Company.
© 2016 General Electric Company. First published March 2016.

All goods and services are sold subject to the terms and conditions of sale of the company within GE Healthcare which supplies them. A copy of these terms and conditions is available on request. Contact your local GE Healthcare representative for the most current information.

GE Healthcare Bio-Sciences AB, Björkgatan 30, 751 84 Uppsala, Sweden

GE Healthcare Europe, GmbH, Munzinger Strasse 5, D-79111 Freiburg, Germany

GE Healthcare Bio-Sciences Corp., 100 Results Way, Marlborough, MA 01752 USA

GE Healthcare Dharmacon, Inc., 2650 Crescent Dr, Lafayette, CO 80026 USA

HyClone Laboratories, Inc., 925 W 1800 S, Logan, UT 84321 USA

GE Healthcare Japan Corporation, Sanken Bldg., 3-25-1, Hyakunincho Shinjuku-ku, Tokyo 169-0073 Japan

For local office contact information, visit www.gelifesciences.com/contact

29184605 AA 03/2016

GE Healthcare UK Limited
Amersham Place
Little Chalfont
Buckinghamshire, HP7 9NA
UK